

נתוני חומרי גלם אברסיביים

PROPERTY	ENGLISH UNITS	METRIC UNITS
Tensile Strength	16.000-18.000 psi	110-124 n/mm ²
Elongation	20-35%	20-35%
Tensile Modulus	200.000-250.000 psi	1380-1790 n/mm ²
Tensile Modulus		
73°F (23°C)		
100% RH	120.000-150.000 psi	830-1020 n/mm ²
Blend Recovery	80-85%	80-85%
Density	1.26 gs/cc	1.26 gs/cc
Melting Point	410°F (210°C)	410°F (210°C)
Water Absorption	1.3%	1.3%
Water Absorption		
73°F (23°C)		
100% RH	2.8%	2.8%

Unless indicated measured 73°F (23°C). 50% RH