

נתוני חומרי הגלם הסינטטיים

Inherent Bend Recovery Chart	
(Standard Test)	
Material	Bend Recovery (%)
Nylon 6,12	92
Nylon 6,6	90
Hog Bristle	92
Horse Hair	88
Tampico	40
Polystyrene	35
Polypropylene	75
Polyvinylchloride-Polyvinyl Acetate	50
Polyvinylidene Chloride	82